



Europäisches **Patentamt**

European **Patent Office** Office européen des brevets

REC'D 24 SEP 2003 WIPO

	P&S-DE zugestellt
am	1 6. April 2003
Frist	

Bescheinigung

Certificate

Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application conformes à la version described on the following page, as originally filed.

Les documents fixés à cette attestation sont Initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr.

Patent application No. Demande de brevet n°

02256348.0

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN COMPLIANCE WITH RULE 17.1(a) OR (b)

> Der Präsident des Europäischen Patentamts; Im Auftrag

For the President of the European Patent Office Le Président de l'Office européen des brevets p.o.

R C van Dijk



43

Europäisches Patentamt



Office européen des brevets

Anmeldung Nr:

Application no.: 02256348.0

Demande no:

Anmeldetag:

Date of filing:

Date de dépôt:

12.09.02

/.u_

IP & S-DE zugestellt am 16. April 2003

Frist

Anmelder/Applicant(s)/Demandeur(s):

Philips Corporate Intellectual Property GmbH

20099 Hamburg
ALLEMAGNE
Koninklijke Philips Electronics N.V.
Groenewoudseweg 1
5621 BA Eindhoven
PAYS-BAS

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention: (Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung. If no title is shown please refer to the description. Si aucun titre n'est indiqué se referer à la description.)

Means for suppression of pass-band ripple in bulk acoustic wave filters

In Anspruch genommene Prioriät(en) / Priority(ies) claimed /Priorité(s) revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/Classification internationale des brevets:

нозн/

Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of filling/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR IE IT LI LU MC NL PT SE SK TR

15

20

PHDE020206 EP-P

5.7/13

ipas-de zugestellt 1 6. April 2003 Frist

IP&S-DE AACHEN

DESCRIPTION

Means for suppression of pass-band ripple in bulk acoustic wave filters

Bulk acoustic wave filters are constructed of bulk acoustic wave resonators which can be connected in a ladder or lattice type configuration. Alternatively also acoustically coupled and stacked crystal resonator configurations can be used to shape the filter curve. To de-couple the resonator from the substrate either acoustic Bragg reflectors consisting of $\lambda/4$ multilayers can be used. Alternatively the resonator can be isolated from the substrate by using an air gap or by creating a membrane structure by etching away the substrate. However, in membrane type resonator structures spurious membrane modes can be excited which can be suppressed only by shaping the membrane in a special way (irregular shape) and by applying absorption layer consisting of a viscoelastic damping material around the resonator edges to suppress lateral propagating acoustic modes (see eg. US006150703A).

Bragg reflectors have the advantage of having less spurious modes since mainly the longitudinal extensional modes is excited in the piezoelectric film inside the resonator. However, the reflector has to have a high reflection coefficient near 100% in the passband of the BAW filter to avoid that acoustic energy penetrates into the substrate and causes vibrations of the substrate. To get a high reflection coefficient of the reflector, one needs several of pairs of layers of material having high and low acoustic impedance (typical 5). For some applications (IF filters), which do not require extremely low insertion loss, the number of pairs in the reflector could be reduced. This would save processing time and manufacturing cost. However, then more acoustic energy would pass towards the substrate and the vibrations of the substrate could be seen as a strong ripple in the pass-band of the BAW filter.

Aim of the invention is to provide means to reduce this pass-band ripple by absorbing or scattering the longitudinal acoustic wave traveling though the substrate. Below the means are listed which by which the pass-band ripple can be reduced:

The figures show different BAW resonators with absorbing layer to suppress passband ripple in a BAW resonator filter. 1= top electrode, 2= piezoelectric layer(e.g. AlN), 3 = bottom electrode, 4 = Bragg reflector, 5=absorbing layer, 6 = substrate, 7=roughened substrate.

5

- 1. Roughening rear side of substrate (Fig. 1).
- 2. Adding an absorbing layer (e.g. epoxy glue) to the rear side of the substrate (Fig. 2).
- 3. Adding an absorbing layer on front of substrate and below Bragg reflector (Fig. 3).
- 4. Combination of means 1-3.

10

In Fig.4 is shown an example of a BAW resonator filter curve in which the pass-band ripple is reduced by adding an absorbing layer on top of substrate (e.g.a glass substrate and epoxy glue as absorbing layer). The Bragg reflector is consisting of alternate \$\mathcal{L}/4\$ layers of SiO2 and Ta2O5. On top of this reflector the bottom electrode Pt and the piezoelectric film is stacked. As top electrode is used Al. As can be seen, the pass-band is free of any ripple. This is due to the use of an absorbing layer underneath the Bragg reflector on top of the glass substrate. The absorbing layer used was epoxy glue. Other materials which can be used as acoustic absorber: viscoeleastic materials such as polyimide, all kind of glue, rubber, plastic materials, porous media, porous thin films etc. in which either acoustic absorption mechanisms are dominant or acoustic scattering occurs.

25

-3-

CLAIMS

- Bulk acoustic wave filters comprising a substrate with a front side and rear side and a Bragg reflector wherein the rear side of the substrate is roughened.
- 2. Bulk acoustic wave filters according to claim 1,
- 5 comprising also an absorbing layer between the front side of the substrate and the Bragg reflector.
 - 3. Bulk acoustic wave filters according to claim 1, comprising also an absorbing layer at the rear front side of the substrate

10

15



ABSTRACT

Means for suppression of pass-band ripple in bulk acoustic wave filters

Bulk acoustic wave filters comprising a substrate with a front side and rear side and a Bragg reflector wherein the rear side of the substrate is roughened.

5

Fig. 1

10







Fig. 1








Fig. 2






Fig. 3

5.12/13




Fig. 4

This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

□ BLACK BORDERS
□ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
□ FADED TEXT OR DRAWING
□ BLURRED OR ILLEGIBLE TEXT OR DRAWING
□ SKEWED/SLANTED IMAGES
□ COLOR OR BLACK AND WHITE PHOTOGRAPHS
□ GRAY SCALE DOCUMENTS
□ LINES OR MARKS ON ORIGINAL DOCUMENT
□ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

IMAGES ARE BEST AVAILABLE COPY.

OTHER:

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.